

CeramicSteel Flow™

CeramicSteel Flow is large format writing board system that allows you to leverage vertical space. A series of vertically oriented, full-height writing panels can be finished with an aluminum outer frame or frameless option that is sealed with a durable lacquer to match the surface color.

Dimensions	Thickness	Weight
1185 mm x 1830 mm / 47 in x 72 in	13 mm / 0.51 in	28 kg / 61.7 lbs
1185 mm x 2420 mm / 47 in x 95 in	13 mm / 0.51 in	37 kg / 81.5 lbs

*Dimensions are nominal

Color		Finish	Finish Code	Approximate RAL Color	Approximate Pantone® Color
Arctic White		Gloss	7671	9003	11-4800 TPG
White 6100 H		Gloss	7655	9010	Cool Gray 1C
Hygienic White		Gloss	PV09	9003	Cool Gray 1C
Gray 6502 C		Chalk	7661	7047	Black 7C
Surface Design		Gloss	Available with Custom Graphics	–	–

Element	Material
Face	CeramicSteel writing surface
Core	Water-resistant MDF 12 mm
Back	Aluminum

Panel Property	Testing Standard	Unit	Value
Panel Thickness	EN 438-2:5	mm	13.1 ± 0.5
Length Tolerance	EN 438-2:6	mm	± 1
Width Tolerance	EN 438-2:6	mm	± 1
Squareness	Difference in diagonals of panels	mm	± 1.5
Fire Resistance	ASTM E84-16	–	Class A, 15/15
General Safety Requirements	EN 14434 §6	–	Smooth and round edges, no risk of injury
General Safety Requirements	EN 14434 §6	–	No risk of pinching/ squeezing
General Safety Requirements	EN 14434 §6	–	No small detachable parts
Vertical Downwards Static Load	EN 14434 §9.1.3	–	No failure, loss of use or fracture at 250 N
Vertical Upwards Static Load	EN 14434 §9.1.4	–	No failure, loss of use or fracture at 200 N
Surface Deflection	EN 14434 §9.5	–	Deformation under 50 N load < 5 mm
Sharp edges enameled steel topside	UL1439	–	Smooth and round edges, to not cause a cut - type injury
Sharp edges enameled steel bottomside	UL1439	–	Smooth and round edges, to not cause a cut - type injury
Enamel Edge Chip Off	–	mm	Max. 0.5
Flatness	–	–	0,15%
Weight (typical)	–	kg/m ²	13

Surface Property	Testing Standard	Unit	Value
Gloss – Marker Surface	ISO 2813 / ASTM D523 20°	GU	65-80
Gloss – Chalk Surface	ISO 2813 / ASTM D523 60°	GU	3.5–9.5
Color Tolerance	ISO 7724 / ASTM D2244-02	E ⁹⁴	≤ 1.5 (compared to reference sample)
Orange Peel	ISO 2813 / ASTM D523	mm	Short Wave ≤ 55 Long Wave ≤ 25 Distinctness of Image ≥ 60
Mohs Hardness	EN 15771	–	Min. 5
Scratch Resistance	ISO 15695	N	Min. 7
Pencil Hardness	ASTM D-3363	–	> 9H
Wear Resistance	ASTM C501	g	Max. 0.1 (abrasive S33 1 kg/1000 rev)
Impact	ISO 4532	–	No damage over 2 mm after 24h (20N load)
Coating Adhesion	EN 10209 Annex D	–	Min. Class 3
Total Thickness Enamel Top Coatings	ISO2178/ASTM B499	µm	85–120
Steel Thickness	–	mm	0.35 ± 0.03
Thickness Backside Enamel Coating	ISO2178/ASTM B499	µm	25–50
Acid Resistance	ISO 28706-1-9	–	Min. A
Chemical Resistance	ISO 28706-1-11	–	Min. A
Dry Erasability	PV 41.803	E ⁹⁴	≤ 1.5
Writability and Erasability	EN ISO 28762 §8.2	E ⁹⁴	≤ 0.5
Graffiti Resistance	EN ISO 28762 §9	–	No color or gloss change after cleaning

SURFACEMATTERS™

©2024 Polyvision Corporation. All rights reserved. Trademarks used herein are the trademarks of Polyvision Corporation or their respective owner. Polyvision Corporation reserves the right to make changes in product design, construction or detail, and to discontinue any product or material without notice.

*Pantone is a trademark of Pantone LLC. Use of the Pantone trademark does not imply an endorsement, sponsorship, or affiliation.

polyvision.com



03-13-2024 ENG